

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 090 684 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
11.04.2001 Bulletin 2001/15

(21) Application number: 00308488.6

(22) Date of filing: 27.09.2000

(51) Int Cl.7: **B01J 23/887**, B01J 27/057,
B01J 35/00, B01J 37/02,
C07C 51/215, C07C 45/33,
C07C 57/04

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 01.10.1999 US 157283 P

(71) Applicant: **ROHM AND HAAS COMPANY**
Philadelphia, Pennsylvania 19106-2399 (US)

(72) Inventor: **Lin, Manhua**
Maple Glen, Pennsylvania 19002 (US)

(74) Representative: **Buckley, Guy Julian**
ROHM AND HAAS (UK) LTD.
European Operations Patent Department
Lennig House
2 Mason's Avenue
Croydon CR9 3NB (GB)

(54) **A catalyst useful for the gas phase oxidation of alkanes, alkenes or alcohols to unsaturated aldehydes or carboxylic acids**

(57) A catalyst useful for oxidation reactions is disclosed. The catalyst is useful for the gas phase oxidation

of alkanes, propylene, acrolein, or isopropanol to unsaturated aldehydes or carboxylic acids.

EP 1 090 684 A1

Description

[0001] This invention relates to a catalyst which is useful for oxidation reactions. In particular, the invention relates to a catalyst which is efficient in converting alkanes, alkenes, or alcohols to unsaturated aldehydes and acids, and a process for preparing unsaturated aldehydes and acids using the catalyst.

[0002] Unsaturated aldehydes and acids are important commercial chemicals. Of particular importance is (meth)acrylic acid. The highly reactive double bond and acid function of (meth)acrylic acid makes it especially suitable as a monomer which may be polymerized alone or with other monomers to produce commercially important polymers. These unsaturated acids are also useful as a starting material for esterification to produce commercially important (meth)acrylate esters. Materials derived from (meth)acrylic acid or esters of (meth)acrylic acids are useful as plastic sheets and parts, paints and other coatings, adhesives, caulks, sealants, plastic additives, and detergents as well as other applications.

[0003] The production of unsaturated acids by oxidation of an olefin is well known in the art. Acrylic acid, for instance, may be commercially manufactured by the gas phase oxidation of propylene. It is also known that unsaturated carboxylic acids may also be prepared by oxidation of alkanes. For instance, acrylic acid may be prepared by the oxidation of propane. Such a process is especially desirable because alkanes generally have a lower cost than olefins. For example, at the time of filing this application propylene costs approximately three times more than propane. A suitable economic process for the oxidation of alkanes, as well as from oxidation of starting materials, to unsaturated aldehydes which is commercially viable has yet to be achieved.


[0004] There is continuing research in the area of new catalysts and starting materials for the production of (meth)acrylic acid and (meth)acrolein. This research generally is directed at reducing the cost of raw materials or increasing the yield of the oxidation process.

[0005] One impediment for the production of a commercially viable process for the catalytic oxidation of an alkane to an unsaturated acid is the identification of a catalyst having adequate conversion and suitable selectivity, thereby providing sufficient yield of the unsaturated acid end-product. United States Patent No. 5,380,933 discloses a method for preparing a catalyst useful in the gas phase oxidation of an alkane to an unsaturated carboxylic acid. In the disclosed method, a catalyst was prepared by combining ammonium metavanadate, telluric acid and ammonium paramolybdate to obtain a uniform aqueous solution. To this solution was added ammonium niobium oxalate to obtain a slurry. The water was removed from the slurry to obtain a solid catalyst precursor. The solid catalyst precursor was molded into a tablet, sieved to a desired particle size and then calcined at 600°C under a nitrogen stream to obtain the desired catalyst.

[0006] Co-pending United States Patent Application No. 09/316007 disclosed a process for preparing a catalyst for catalyzing an alkane into an unsaturated aldehyde or carboxylic acid wherein phase segregation was minimized and improvement in selectivity, conversion, and yield were achieved.

[0007] Despite the disclosure of the references, there is a continuing need for new catalysts and improved processes for the production of (meth)acrylic acid and/or (meth)acrolein.

[0008] In one aspect of the present invention, there is provided a catalyst having the formula:



wherein $0.25 < a < 0.98$, $0.003 < m < 0.5$, $0.003 < n < 0.5$, $0.003 < x < 0.5$, and o is dependent on the oxidation state of the other elements, and A is at least one of Mo, W, Fe, Nb, Ta, Zr, and Ru; M is at least one of V, Ce, and Cr; N is at least one of Te, Bi, Sb, and Se; and X is at least one of Nb, Ta, W, Ti, Al, Zr, Cr, Mn, Fe, Ru, Co, Rh, Ni, Pd, Pt, Sb, Bi, B, In, and Ce; wherein the catalyst exhibits at least two crystal phases, one phase including major x-ray diffraction peaks at 22.1, 28.2, 36.2, 45.2, 50.5, 54.2, 55.4, and 58.5, and a second phase including major x-ray diffraction peaks at 22.1, 27.2, 35.3, 45.2, and 51.1.

[0009] In a second aspect of the present invention, there is provided a process for preparing unsaturated aldehydes and acids including subjecting an alkane to catalytic oxidation in the presence of a catalyst having the formula



wherein $0.25 < a < 0.98$, $0.003 < m < 0.5$, $0.003 < n < 0.5$, $0.003 < x < 0.5$, and o is dependent on the oxidation state of the other elements, and A is at least one of Mo, W, Fe, Nb, Ta, Zr, and Ru; M is at least one of V, Ce, and Cr; N is at least one of Te, Bi, Sb, and Se; and X is at least one of Nb, Ta, W, Ti, Al, Zr, Cr, Mn, Fe, Ru, Co, Rh, Ni, Pd, Pt, Sb, Bi, B, In, and Ce; wherein the catalyst exhibits at least two crystal phases, one phase including major x-ray diffraction peaks at 22.1, 28.2, 36.2, 45.2, 50.5, 54.2, 55.4, and 58.5, and a second phase including major x-ray diffraction peaks at 22.1, 27.2,

35.3, 45.2, and 51.1.

[0010] In a third aspect, the present invention provides a process for preparing unsaturated aldehydes and acids including subjecting a compound selected from propylene, acrolein, and isopropanol to catalytic oxidation in the presence of a catalyst having the formula:



wherein $0.25 < a < 0.98$, $0.003 < m < 0.5$, $0.003 < n < 0.5$, $0.003 < x < 0.5$, and o is dependent on the oxidation state of the other elements, and A is at least one of Mo, W, Fe, Nb, Ta, Zr, and Ru; M is at least one of V, Ce, and Cr; N is at least one of Te, Bi, Sb, and Se; and X is at least one of Nb, Ta, W, Ti, Al, Zr, Cr, Mn, Fe, Ru, Co, Rh, Ni, Pd, Pt, Sb, Bi, B, In, and Ce; wherein the catalyst exhibits at least two crystal phases, one phase including major x-ray diffraction peaks at 22.1, 28.2, 36.2, 45.2, 50.5, 54.2, 55.4, and 58.5, and a second phase including major x-ray diffraction peaks at 22.1, 27.2, 35.3, 45.2, and 51.1.

[0011] Figure 1 depicts the x-ray diffraction (XRD) spectra of major XRD peaks for catalysts 1-7.

[0012] As used herein, the expression "(meth)acrylic acid" is intended to include both methacrylic acid and acrylic acid within its scope. In a like manner, the expression "(meth)acrylates" is intended to include both methacrylates and acrylates within its scope and the expression "(meth)acrolein" is intended to include both acrolein and methacrolein within its scope.

[0013] As used herein the terminology "(C₃-C₈) alkane" means a straight chain or branched chain alkane having from 3 to 8 carbon atoms per alkane molecule.

[0014] As used herein the term "mixture" is meant to include within its scope all forms of mixtures including, but not limited to, simple mixtures as well as blends, alloys, etc.

[0015] For purposes of this application "% conversion" is equal to (moles of consumed alkane/moles of supplied alkane) X 100; "% selectivity" is equal to (moles of formed desired unsaturated carboxylic acid or aldehyde/moles of consumed alkane) X 100; and "% yield" is equal to (moles of formed desired unsaturated carboxylic acid or aldehyde/moles of supplied alkane) X (carbon number of formed desired unsaturated carboxylic acid or aldehyde/ carbon number of the supplied alkane) X 100.

[0016] For purposes of this application by "solution" is meant that greater than 95 percent of metal solid added to a solvent is dissolved. It is to be understood that the greater the amount of metal solid not initially in solution, the poorer the performance of the catalyst derived therefrom will be.

[0017] As recited above, a catalyst having at least two specific crystal phases is disclosed. The two crystal phases may be obtained either through a specific method of preparation of the catalyst or through varying the composition of the catalyst.

[0018] In a first step of the method of preparation of the catalyst, a solution is formed by admixing metal compounds, at least one of which contains oxygen, and at least one solvent in appropriate amounts to form the solution. Generally, the metal compounds contain elements A, M, N, X, and O. In one embodiment, A is at least one of Mo, W, Fe, Nb, Ta, Zr, and Ru; M is at least one of V, Ce, and Cr; N is at least one of Te, Bi, Sb, and Se; and X is at least one of Nb, Ta, W, Ti, Al, Zr, Cr, Mn, Fe, Ru, Co, Rh, Ni, Pd, Pt, Sb, Bi, B, In, and Ce. In a preferred embodiment, A is at least one of Mo and W; M is at least one of V, Ce, and Cr; N is at least one of Te, Bi, and Sb; and X is at least one of Nb, Ta, and Zr. In a more preferred embodiment, A is Mo, M is V, N is Te and X is Nb.


[0019] Suitable solvents include water, alcohols including, but not limited to, methanol, ethanol, propanol, and diols etc, as well as other polar solvents known in the art. Generally, water is preferred. The water is any water suitable for use in chemical synthesis including, without limitation, distilled water and deionized water. The amount of water present is that amount sufficient to keep the elements substantially in solution long enough to avoid or minimize compositional and/or phase segregation during the preparation steps. Accordingly, the amount of water will vary according to the amounts and solubility of materials combined. However, as stated above the amount of water must be sufficient to insure an aqueous solution is formed and not a slurry at the time of mixing.

[0020] Once the aqueous solution is formed, the water is removed by a combination of any suitable methods known in the art to form a catalyst precursor. Such methods include, without limitation, vacuum drying, freeze drying, spray drying, rotary evaporation, and air drying. Vacuum drying is generally performed at pressures ranging from 10 to 500 mm/Hg. Freeze drying typically entails freezing the solution, using for instance liquid nitrogen, and drying the frozen solution under vacuum. Spray drying is generally performed under an inert atmosphere such as nitrogen, argon, or air with an inlet temperature ranging from 125°C to 200°C and an outlet temperature ranging from 75°C to 150°C. Rotary evaporation is generally performed at a bath temperature of from 25°C to 90°C and a pressure of from 10 mm/Hg to 760 mm/Hg, preferably at a bath temperature of from 40°C to 90°C and a pressure from 10 mm/Hg to 350 mm/Hg, more preferably from 40°C to 60°C and a pressure of from 10 mm/Hg to 40 mm/Hg. Air drying may occur at temperatures ranging from 10°C to 90°C. Rotary evaporation or air drying are generally preferred.

[0021] Once obtained, the catalyst precursor is calcined under an inert atmosphere. The inert atmosphere may be any material which is substantially inert, i.e., does not react or interact with, the catalyst precursor. Suitable examples include, without limitation, nitrogen, argon, xenon, helium or mixtures thereof. Preferably, the inert atmosphere is argon or nitrogen, more preferably argon. The inert atmosphere may flow over the surface of the catalyst precursor or may not flow (a static environment). It is important to understand that by non-flow atmosphere is meant that the inert gas is not allowed to flow over the surface of the catalyst precursor. It is preferred that the inert atmosphere not flow over the surface of the catalyst precursor. However, when the inert atmosphere does flow over the surface of the catalyst precursor, the flow rate can vary over a wide range, for example, at a space velocity from 1 to 500 hr⁻¹.

[0022] The calcination is typically done at a temperature of from 350°C to 850°C, preferably from 400°C to 700°C, more preferably from 500°C to 640°C. The calcination is typically performed for an amount of time suitable to form the catalyst. In one embodiment, the calcination is performed from 0.5 to 30 hours, preferably from 1 to 25 hours and more preferably from 1 to 15 hours.

[0023] With calcination a catalyst is formed having the formula



wherein A, M, N, and X are as described above. Molar ratios, a, m, n, and x are typically, from 0.25<a<0.98, 0.003<m<0.5, 0.003<n<0.5, and 0.003<x<0.5; preferably 0.35<a<0.87, 0.045<m<0.37, 0.020<n<0.27, and 0.005<x<0.35. The catalyst prepared will exhibit at least two crystal phases, one phase including major x-ray diffraction peaks at 22.1, 28.2, 36.2, 45.2, 50.5, 54.2, 55.4, and 58.5, and a second phase including major x-ray diffraction peaks at 22.1, 27.2, 35.3, 45.2, and 51.1. The second phase further includes x-ray diffraction peaks at 7.9, 9.1, and 29.2. Such major peaks and peaks are more completely defined in Table 1 (XRD Peaks of Phase-A) and Table 2 (XRD Peaks of Phase-B) following.

Table 1

diffraction angle(°)	22.1	28.2	36.2	45.2	50.0	54.2	55.4	58.5
Relative Intensity	100	80-180	5-60	2-40	2-50	2-40	2-40	2-40

Table 2

diffraction angle(°)	7.9	9.1	22.1	27.2	29.2	35.3	45.2	51.1
Relative Intensity	2-30	2-30	100	15-80	2-30	2-30	2-40	2-40

[0024] The molar ratio, "o", i.e., the amount of oxygen (O) present, is dependent on the oxidation state of the other elements in the catalyst. However, typically "o" is from 3 to 4.7, based on the other elements present in the catalyst.

[0025] If the composition of the catalyst is varied outside of the ranges defined above, the catalyst will not exhibit both x-ray diffraction phases.

[0026] The catalyst of this invention may be used as a solid catalyst alone or may be utilized with a suitable support such as, without limitation, silica, alumina, titania, aluminosilicate, diatomaceous earth, or zirconia. The shape of the catalyst can be any suitable shape and will depend upon the particular application of the catalyst. In a like manner, the particle size of the catalyst may be any suitable particle size depending on the particular use of the catalyst.

[0027] In the second aspect of the present invention, there is provided a process for preparing unsaturated aldehydes and acids including subjecting an alkane to catalytic oxidation in the presence of the catalyst described above.

[0028] The starting materials for this process are generally an alkane gas or gases and at least one oxygen-containing gas. It is preferred that the starting materials also include steam. Accordingly, a starting material gas is supplied to the system which includes a gas mixture of at least one alkane and steam. The at least one oxygen-containing gas may be included in this mixture or be supplied separately. Furthermore, a diluting gas such as an inert gas including, without limitation, nitrogen, argon, helium, steam, or carbon dioxide may also be included. The diluting gas may be used to dilute the starting material and/or to adjust the space velocity, the oxygen partial pressure, and the steam partial pressure.

[0029] Suitable molar ratios of the alkane/oxygen/diluting gas/water in the starting material gas mixture are known in the art as well as the feed ratio of alkane/air/steam. For instance suitable ranges are disclosed in U.S. Patent No. 5,380,933.

[0030] The starting material alkane is generally any alkane suitable for gas phase oxidation into an unsaturated aldehyde or acid. Generally, the alkane is a C₃-C₈ alkane, preferably propane, isobutane or n-butane, more preferably

propane or isobutane, most preferably propane. Furthermore, in another embodiment the alkane may be a mixture of alkanes including C_3-C_8 alkanes as well as lower alkanes such as methane and ethane.

[0031] The at least one oxygen-containing gas used may be pure oxygen gas, an oxygen containing gas such as air, an oxygen enriched gas, or a mixture thereof.

[0032] In a preferred embodiment, the starting material is a gas mixture of propane, air, and steam. The starting gas mixture is subjected to catalytic oxidation in the presence of the catalyst of the present invention. The catalyst may be in a fluidized bed or a fixed bed reactor. The reaction is generally conducted under atmospheric pressure, but may be conducted under elevated or reduced pressure. The reaction temperature is generally from 200°C to 550°C, preferably 300°C to 480°C, more preferably 350°C to 440°C. The gas space velocity is generally 100 to 10,000 hr^{-1} , preferably 300 to 6,000 hr^{-1} , more preferably 300 to 3,000 hr^{-1} .

[0033] Also, in the method of the present invention it is to be understood that an unsaturated aldehyde may also be formed. For instance when propane is the starting alkane, acrolein may be formed and when isobutane is the starting alkane, methacrolein may be formed.

[0034] In the third aspect of the present invention, there is provided a process for preparing unsaturated aldehydes and acids including subjecting a compound selected from propylene, acrolein, and isopropanol to catalytic oxidation in the presence of the catalyst described above. The process is run in the same manner as described above for the conversion of alkanes to unsaturated aldehydes or acids, except propylene, acrolein, or isopropanol is substituted for the alkane. Also, the reaction temperature is generally from 150°C to 500°C. For propylene and isopropanol the reaction temperature is preferably 250°C to 400°C, and for acrolein preferably 180°C to 350°C. The gas space velocity is generally 100 to 10,000 hr^{-1} , preferably 300 to 6,000 hr^{-1} .

[0035] Abbreviations used throughout this application are:

°C = degrees Centigrade	mm = millimeters	Hg = Mercury
g = grams	cm = centimeters	mmole = millimoles
% = percent by weight	ml/min = milliliters per minute	
N ₂ = nitrogen		

[0036] The following examples illustrate the process of the present invention. Based on the amount of starting material used, if there was no compositional segregation, or there was no loss of certain elements during the preparation steps, all of the catalyst samples prepared as follows should have an empirical formula of $Mo_1V_{0.3}Te_{0.23}Nb_{0.08-0.12}O_n$ where n is determined by the oxidation state of the other elements. The solutions or slurries containing the desired metal elements were prepared by heating the appropriate compounds in water at a temperature ranging from 25°C to 95°C. When necessary, the solutions or slurries were cooled to temperatures ranging from 25°C to 60°C. The water was then removed from the solutions or slurries by the appropriate drying method at pressures ranging from 760 mm/Hg to 10 mm/Hg.

Example 1

[0037] A catalyst-1 with the empirical formula of $Mo_1V_{0.3}Te_{0.23}Nb_{0.10}$ was prepared as follows. In a flask containing 420 g of water, 25.8 g of ammonium heptamolybdate tetrahydrate (Aldrich Chemical Company), 5.1 g of ammonium metavanadate (Aldrich Chemical Company) and 7.7 g of telluric acid (Aldrich Chemical Company) were dissolved upon heating to 80°C. After cooling to 40°C, 121.3 g of an aqueous solution of niobium oxalate (Reference Metals Company) containing 17.3 mmole of niobium was mixed to obtain a solution. The water of this solution was removed via a rotary evaporator with a warm water bath at 50°C and 28 mm/Hg to obtain 46 g of catalyst precursor solid.

[0038] Twenty g of the catalyst precursor solid was calcined in a covered crucible pre-purged with argon, in a non-flow environment at 600°C for 2 hours. The oven had previously been heated to 200°C and held for one hour, then ramped to 600°C. During the calcination, the covered crucible was in a covered beaker with an Ar space velocity of 57 hr^{-1} . Because of the covered crucible, the argon did not flow over the precursor surface, but rather served to insure that the atmosphere outside the crucible remained argon. The atmosphere inside the crucible remained argon and off gasses from the catalyst. The catalyst thus obtained was ground to a fine powder and pressed in a mold and then broken and sieved to 10-20 mesh granules.

[0039] The catalyst (13.4 g) was packed into a 1.1 cm inside diameter stainless steel U-tube reactor for gas phase propane oxidation. The oxidation was conducted with a reactor bath (molten salt) temperature of 390°C, a feed ratio of propane/air/steam of 1/15/14, and a space velocity of 1,200 hr^{-1} . The effluent from the reactor was condensed to separate the liquid phase (the condensable material) and the gas phase. The gas phase was analyzed by gas chromatography ("GC") to determine the propane conversion. The liquid phase was also analyzed by GC for the yield of acrylic acid. The oxidation results are shown in Table 4. The catalyst was also analyzed by x-ray diffraction to determine

its crystalline structure. The main diffraction angles and the corresponding relative intensities are shown in Table 3 and Figure 1.

Example 2

[0040] A catalyst-2 with the empirical formula of $\text{Mo}_1\text{V}_{0.32}\text{Te}_{0.23}\text{Nb}_{0.08}$ was prepared and tested in the same manner as described in example 1. The oxidation results are shown in Table 4. The main diffraction angles and the corresponding relative intensities are shown in Table 3 and Figure 1.

Example 3

[0041] A catalyst-3 with the empirical formula of $\text{Mo}_1\text{V}_{0.3}\text{Te}_{0.2}\text{Nb}_{0.1}$ was prepared and tested in the same manner as described in example 1. The oxidation results are shown in Table 4. The main diffraction angles and the corresponding relative intensities are shown in Table 3 and Figure 1.

Comparative Example 1

[0042] A catalyst-4 with the empirical formula of $\text{Mo}_1\text{V}_{0.20}\text{Te}_{0.40}\text{Nb}_{0.05}$ was prepared and tested in the same manner as described in example 1. The oxidation results are shown in Table 4. The main diffraction angles and the corresponding relative intensities are shown in Table 3 and Figure 1.

Comparative Example 2

[0043] A catalyst-5 with the empirical formula of $\text{Mo}_1\text{V}_{0.31}\text{Te}_{0.46}\text{Nb}_{0.13}$ was prepared and tested in the same manner as described in example 1. The oxidation results are shown in Table 4. The main diffraction angles and the corresponding relative intensities are shown in Table 3 and Figure 1.

Comparative Example 3

[0044] A catalyst-6 with the empirical formula of $\text{Mo}_1\text{V}_{0.50}\text{Te}_{0.50}\text{Nb}_{0.06}$ was prepared and tested in the same manner as described in example 1. The oxidation results are shown in Table 4. The main diffraction angles and the corresponding relative intensities are shown in Table 3 and Figure 1.

Comparative Example 4

[0045] A catalyst-7 with the empirical formula of $\text{Mo}_1\text{V}_{0.3}\text{Te}_{0.23}\text{Nb}_{0.10}$ was prepared as follows. In a flask containing 400 g of water, 18.4 g of ammonium heptamolybdate tetrahydrate (Aldrich Chemical Company), 3.7 g of ammonium metavanadate (Aldrich Chemical Company) and 5.5 g of telluric acid (Aldrich Chemical Company) were dissolved upon heating to 80°C. After cooling to 40°C, 75.5 g of an aqueous solution of niobium oxalate (Reference Metals Company) containing 8.0 mmole of niobium and 9.2 g of oxalic acid was mixed to obtain a solution. The solution was dried in the same manner as described in example 1 to obtain a catalyst precursor. The catalyst precursor was pretreated with air at 315°C for 180 minutes before it was calcined and pressed to granules in the same manner as described in example 1.

[0046] One gram of the catalyst was packed into a 3.8 mm inside diameter quartz tube reactor for gas phase propane oxidation. The oxidation was conducted with a reactor bath temperature of 380°C, a feed ratio of propane/air/steam of 1/96/3, and a space velocity of 1,200 hr⁻¹. The effluent from the reactor was analyzed by IR to determine the propane conversion and AA yield. The oxidation results are shown in Table 4. The main diffraction angles and the corresponding relative intensities are shown in Table 3 and Figure 1.

Table 3

	7.9°	9.1°	22.1°	27.2°	28.3°	29.2	35.3	36.2°	45.2°	50.0°	51.1	54.2	554	58.5
Cat. 1	13	11	100	37	81	16	15	30	28	25	19	17	16	12
Cat. 2	11	8	100	30	89	17	10	30	21	22	14	15	18	12
Cat. 3	14	11	100	39	26	17	13	9	20	11	18	12	8	6
Cat. 4	-	-	100	-	149		-	48	18	41	-	24	25	19
Cat. 5	-	-	100	-	169		-	59	24	42	-	27	27	20
Cat. 6	-	-	100	-	190		-	56	21	45	-	25	25	21
Cat. 7	-	-	100	-	141		-	46	18	38	-	19	21	18

[0047] The data above demonstrates that both x-ray diffraction phases are present in the catalyst when the catalyst is prepared by the method described above and is within the compositional ranges described above. The catalyst does not exhibit both x-ray diffraction phases when prepared by a different method or when the composition falls outside the range described above.

Table 4

Example	Empirical Formula	Conv. (%)	Sel. (%)	Yield (%)
1	$\text{Mo}_1\text{V}_{0.3}\text{Te}_{0.23}\text{Nb}_{0.10}$	73	58	42
2	$\text{Mo}_1\text{V}_{0.32}\text{Te}_{0.23}\text{Nb}_{0.08}$	78	47	37
3	$\text{Mo}_1\text{V}_{0.30}\text{Te}_{0.20}\text{Nb}_{0.10}$	43	43	19
Comp. 1	$\text{Mo}_1\text{V}_{0.20}\text{Te}_{0.40}\text{Nb}_{0.05}$	0.6	50	0.3
Comp. 2	$\text{Mo}_1\text{V}_{0.31}\text{Te}_{0.46}\text{Nb}_{0.13}$	11	58	6.2
Comp. 3	$\text{Mo}_1\text{V}_{0.50}\text{Te}_{0.50}\text{Nb}_{0.06}$	6	22	1.3
Comp. 4	$\text{Mo}_1\text{V}_{0.30}\text{Te}_{0.23}\text{Nb}_{0.10}$	49	5	2.4
Comp. = comparative conv.(%) = percent of propane converted sel.(%) = selectivity of propane conversion to acrylic acid in percent yield(%) = the yield of acrylic acid in percent				

[0048] The data above demonstrates that the catalyst is efficient at converting propane to acrylic acid when the catalyst contains both x-ray diffraction phases. The catalyst is ineffective when only one of the x-ray diffraction phases is present in the catalyst.

Example 4

[0049] Catalyst-2 was tested for oxidation as in example 1, except propylene was substituted for propane. The oxidation was conducted with a reactor bath (molten salt) temperature of 350°C, a feed ratio of propylene/air/steam/nitrogen of 1/35/10/2.8, and a space velocity of 3,600 hr⁻¹. The effluent from the reactor was condensed to separate the liquid phase (the condensable material) and the gas phase. The gas phase was analyzed by gas chromatography ("GC") to determine the propylene conversion. The liquid phase was also analyzed by GC for the yield of acrylic acid. The oxidation results are shown in Table 5.

Comparative Example 5

[0050] Catalyst-4 was tested in the same manner as described in example 4. The oxidation results are shown in Table 5.

Comparative Example 6

[0051] Catalyst-8 with an empirical formula of $\text{Mo}_1\text{V}_{0.3}\text{Te}_{0.23}\text{Nb}_{0.10}$ was prepared from the same starting material as described in example 4. A solution containing 39.5 g of ammonium heptamolybdate tetrahydrate, 7.85 g of ammonium metavanadate and 11.8 g of telluric acid and an ammonium niobium oxalate solution containing 27.7 mmole of niobium was prepared in the same manner described in example 1. This solution was frozen to solid form in an acetone-dry-ice bath and dried under vacuum to obtain 64 g of powdery solid. The powdery catalyst precursor was pressed and sized to granules and was calcined at 600°C for two hours with a steady nitrogen flow.

[0052] The resulting catalyst (42g) was pressed and sized to granules. The catalyst (23 g) was tested in the same way as described in example 4 except at a reactor bath temperature of 390°C and a feed composition of propylene/air/steam volume ratio at 1/15/14. The oxidation results are shown in Table 5.

Table 5

	Temp. (°C)	Conv. (%)	Sel. (%)	Yield (%)
Example 4	350	100	75.3	75.3

Table 5 (continued)

	Temp. (°C)	Conv. (%)	Sel. (%)	Yield (%)
Comp. 5	350	33.2	90.7	30.1
Comp. 6	380	46.2	83.7	38.7
conv.(%) = percent of propylene converted Temp. = temperature sel.(%) = selectivity of propylene conversion to acrylic acid in percent yield(%) = the yield of acrylic acid in percent Comp. = comparative				

[0053] The data above demonstrates that the catalyst is more efficient at converting propylene to acrylic acid when the catalyst contains both x-ray diffraction phases. The catalyst is less effective when only one of the x-ray diffraction phases is present in the catalyst.

Example 5

[0054] Catalyst-2 was tested for oxidation as in example 1, except isopropanol was substituted for propane. The oxidation was conducted with a reactor bath (molten salt) temperature of 350°C, a feed ratio of isopropanol/air/steam/nitrogen of 1/35/10/2.8, and a space velocity of 3,600 hr⁻¹. The effluent from the reactor was condensed to separate the liquid phase (the condensable material) and the gas phase. The gas phase was analyzed by gas chromatography ("GC") to determine the isopropanol conversion. The liquid phase was also analyzed by GC for the yield of acrylic acid. The oxidation results are shown in Table 6.

Comparative Examples 7 and 8

[0055] Catalyst-4 was tested in the same way as described in example 5 except at a reactor bath temperatures of both 320°C and 390°C and a feed composition of isopropanol/air/steam volume ratio at 1/15/14. The oxidation results are shown in Table 6.

Table 6

	Temp. (°C)	Conv. (%)	Sel. (%)	Yield (%)
Example 5	350	100	49.3	49.3
Comp. 7	320	100	18	18
Comp. 8	390	100	30	30
conv.(%) = percent of isopropanol converted Temp. = temperature sel.(%) = selectivity of isopropanol conversion to acrylic acid in percent yield(%) = the yield of acrylic acid in percent Comp. = comparative				

[0056] The data above demonstrates that the catalyst is more efficient at converting isopropanol to acrylic acid when the catalyst contains both x-ray diffraction phases. The catalyst is less effective when only one of the x-ray diffraction phases is present in the catalyst.

Example 6

[0057] Catalyst-2 was tested for oxidation as in example 1, except acrolein was substituted for propane. The oxidation was conducted with a reactor bath (molten salt) temperature of 251°C, a feed ratio of acrolein/air/steam of 1.7/52/47, and a space velocity of 3,600 hr⁻¹. The effluent from the reactor was condensed to separate the liquid phase (the condensable material) and the gas phase. The gas phase was analyzed by gas chromatography ("GC") to determine the acrolein conversion. The liquid phase was also analyzed by GC for the yield of acrylic acid. The oxidation results

are shown in Table 7.

Example 7

- [0058] Catalyst-2 was tested for oxidation as in Example 6, , except the oxidation was conducted with a reactor bath (molten salt) temperature of 220°C. The oxidation results are shown in Table 7.

Comparative Examples 9 and 10

- [0059] Catalyst 4 and catalyst 8 were tested in the same way as described in example 6 except at a reactor bath temperatures of 251°C and 250°C respectively and a feed composition of acrolein/air/steam volume ratio at 1/15/14. The oxidation results are shown in Table 7.


Table 7

	Temp. (°C)	Conv. (%)	Sel. (%)	Yield (%)
Example 6	251	100	81.9	81.9
Example 7	220	99.1	90.2	89.4
Comp. 9	251	84.6	85.5	72.3
Comp. 10	250	97	76	73.7
conv.(%) = percent of acrolein converted Temp. = temperature sel.(%) = selectivity of acrolein conversion to acrylic acid in per- cent yield(%) = the yield of acrylic acid in percent Comp. = comparative				

- [0060] The data above demonstrates that the catalyst is more efficient at converting acrolein to acrylic acid when the catalyst contains both x-ray diffraction phases. The catalyst is less effective when only one of the x-ray diffraction phases is present in the catalyst.

Claims

1. A catalyst comprising:




wherein $0.25 < a < 0.98$, $0.003 < m < 0.5$, $0.003 < n < 0.5$, $0.003 < x < 0.5$, and o is dependent on the oxidation state of the other elements, and A is at least one of Mo, W, Fe, Nb, Ta, Zr, and Ru; M is at least one of V, Ce, and Cr; N is at least one of Te, Bi, Sb, and Se; and X is at least one of Nb, Ta, W, Ti, Al, Zr, Cr, Mn, Fe, Ru, Co, Rh, Ni, Pd, Pt, Sb, Bi, B, In, and Ce; wherein the catalyst exhibits at least two crystal phases, one phase comprising major x-ray diffraction peaks at 22.1, 28.2, 36.2, 45.2, 50.5, 54.2, 55.4, and 58.5, and a second phase comprising major x-ray diffraction peaks at 22.1, 27.2, 35.3, 45.2, and 51.1.

2. The catalyst according to claim 1 wherein the catalyst comprises $0.35 < a < 0.87$, $0.045 < m < 0.37$, $0.020 < n < 0.27$, and $0.005 < x < 0.35$.
3. The catalyst according to claim 1, wherein A is at least one of Mo, and W; M is at least one of V, Ce, and Cr; N is at least one of Te, Bi, and Sb; and X is at least one of Nb, Ta, and Zr.
4. The catalyst according to claim 1, wherein A is Mo, M is V, N is Te, and X is Nb.
5. The catalyst according to claim 1, wherein the second phase further comprises x-ray diffraction peaks at 7.9, 9.1, and 29.2.

6. A process for preparing unsaturated aldehydes and acids comprising subjecting an alkane to catalytic oxidation in the presence of the catalyst of claim 1.
7. The process according to claim 6, wherein the alkane is propane, the unsaturated aldehyde is acrolein.
8. The process according to claim 6, wherein the alkane is propane, the unsaturated acid is acrylic acid.
9. A process for preparing unsaturated aldehydes and acids comprising subjecting a compound selected from propylene, acrolein, and isopropanol to catalytic oxidation in the presence of the catalyst of claim 1.
10. The process according to claim 9, wherein the compound is propylene and the unsaturated aldehyde is acrolein.
11. The process according to claim 9, wherein the compound is propylene and the unsaturated acid is acrylic acid.
12. The process according to claim 9, wherein the compound is acrolein and the unsaturated acid is acrylic acid.
13. The process according to claim 9, wherein the compound is isopropanol and the unsaturated aldehyde is acrolein.
14. The process according to claim 9, wherein the compound is isopropanol and the unsaturated acid is acrylic acid.

FIG. 1





European Patent
Office

PARTIAL EUROPEAN SEARCH REPORT

Application Number

which under Rule 45 of the European Patent Convention EP 00 30 8488
shall be considered, for the purposes of subsequent
proceedings, as the European search report

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 529 853 A (MITSUBISHI CHEM IND) 3 March 1993 (1993-03-03) * page 3, line 14 - line 20 * * page 4, line 7 - line 17 * * examples * * claims 1-5 * * figure 1 *	1-5	B01J23/887 B01J27/057 B01J35/00 B01J37/02 C07C51/215 C07C45/33 C07C57/04
Y	---	6-14	
D,X	US 5 380 933 A (USHIKUBO TAKASHI ET AL) 10 January 1995 (1995-01-10) * column 1, line 5 - line 20 * * column 1, line 60 - column 2, line 28 * * column 2, line 56 - column 3, line 48 * * column 4, line 51 - line 55 * * column 6, line 16 - line 33 * * examples * * claims 1,6-13 * --- -/-	1-9,12	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			B01J C07C
INCOMPLETE SEARCH			
<p>The Search Division considers that the present application, or one or more of its claims, does/do not comply with the EPC to such an extent that a meaningful search into the state of the art cannot be carried out, or can only be carried out partially, for these claims.</p> <p>Claims searched completely:</p> <p>Claims searched incompletely:</p> <p>Claims not searched:</p> <p>Reason for the limitation of the search:</p> <p>see sheet C</p>			
Place of search		Date of completion of the search	Examiner
MUNICH		30 November 2000	Gosselin, D
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 103 (01/95) (P4007)

European Patent
OfficeINCOMPLETE SEARCH
SHEET CApplication Number
EP 00 30 8488

Claim(s) searched completely:

4

Claim(s) searched incompletely:

1-3,5-14

Reason for the limitation of the search:

Present claim 1 relates to an extremely large number of possible compounds. Support within the meaning of Article 84 EPC and disclosure within the meaning of Article 83 EPC is to be found, however, for only the compounds according to claim 4 of the application (cf examples). In the present case, the claims so lack support, and the application so lacks disclosure, that a meaningful search over the whole of the claimed scope is impossible. Consequently, the search has been carried out those parts of the claims which appear to be supported and disclosed, namely those parts relating to the catalysts of claim 4.

PARTIAL EUROPEAN SEARCH REPORT

Application Number
EP 00 30 8488

DOCUMENTS CONSIDERED TO BE RELEVANT			CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	
P,X	EP 0 962 253 A (ROHM & HAAS) 8 December 1999 (1999-12-08) * paragraph [0001] - paragraph [0003] * * paragraph [0017] - paragraph [0022] * * paragraph [0028] * * paragraph [0033] - paragraph [0054] * * claims 1-5,9-16 * ---	1-8	
Y	US 5 198 580 A (BARTEK JOSEPH P ET AL) 30 March 1993 (1993-03-30) * claims *	6-8	
Y	US 3 936 565 A (ODA YOSHIO ET AL) 3 February 1976 (1976-02-03) * claims; example 86 * -----	9-14	TECHNICAL FIELDS SEARCHED (Int.Cl.7)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 30 8488

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

30-11-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0529853 A	03-03-1993	BR 9203080 A	30-03-1993
		CN 1069723 A,B	10-03-1993
		DE 69208565 D	04-04-1996
		DE 69208565 T	26-09-1996
		JP 5279313 A	26-10-1993
		SG 42912 A	17-10-1997
		US 5472925 A	05-12-1995
		US 5281745 A	25-01-1994
		JP 5208136 A	20-08-1993
US 5380933 A	10-01-1995	JP 7010801 A	13-01-1995
		JP 6279351 A	04-10-1994
		DE 69402567 D	22-05-1997
		DE 69402567 T	27-11-1997
		EP 0608838 A	03-08-1994
EP 0962253 A	08-12-1999	BR 9901568 A	21-12-1999
		CN 1236672 A	01-12-1999
		JP 2000024501 A	25-01-2000
US 5198580 A	30-03-1993	NONE	
US 3936505 A	03-02-1976	JP 944881 C	20-03-1979
		JP 48085519 A	13-11-1973
		JP 53028407 B	15-08-1978
		JP 926249 C	22-09-1978
		JP 48103506 A	25-12-1973
		JP 53005648 B	01-03-1978
		JP 943260 C	15-03-1979
		JP 49000212 A	05-01-1974
		JP 53023808 B	17-07-1978
		DE 2308782 A	25-10-1973
		FR 2173203 A	05-10-1973
		GB 1377325 A	11-12-1974
		IT 979361 B	30-09-1974
		US 4025565 A	24-05-1977

EPO FORM P0159

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82